

NSE

SAFE FOR
DRINKING
WATER CONTACT

#FP-S1G

Net Wt. 1.33 oz. (37.7g)

NEW

Pow-R Stick[®]
Steel Reinforced Epoxy

Steel Hard
15 MINUTE REPAIR
Epoxy Putty

Made in the U.S.A.

Fernco
Inc.


www.fernco.com

GREY COLOR • GREY COLOR • GREY COLOR

Pow-R Stick is a hand workable, steel reinforced epoxy putty that cures steel-hard within minutes of mixing. Extremely tough and durable with exceptional adhesion to a wide range of materials.

Physical Properties:

Density 1.75
Compression Strength..... 12,801 psi
Tensile Strength 1,209 psi
Modular Elasticity..... 6x10⁵ psi
Shear Strength..... 700 psi
Izod Impact..... .03 ft. lbs/in a notch
Hardness (Shore D) 85
Max Temp..... 392° F / 200° C

Pow-R Stick es una masilla epoxy que se puede usar con las manos y que cuenta con refuerzo de acero la cual se endurece en unos pocos minutos. Tiene gran resistencia y durabilidad con una adherencia excepcional a una amplia gama de materiales.

Propiedades físicas:

Densidad 1.75
Resistencia a la compresión..... 12,801 psi
Resistencia a la tensión 1,209 psi
Elasticidad modular 6 x 10⁵ psi
Resistencia al corte 700 psi
Impacto Izod .. 0.03 ft. lbs/en una muestra
Dureza de la goma (Shore D) 85
Temperatura máxima..... 392° F / 200° C

Fernco, Inc. • 300 S. Dayton Street Davison, MI 48423 • www.fernco.com



DIRECTIONS - READ COMPLETELY BEFORE STARTING:

To keep hands clean, moisten with water prior to kneading.

- For best adhesion, clean and roughen the bond area prior to application.
- Twist, break or cut off the desired amount for repair
- Knead the putty to a uniform color - with no specs
- Putty should be in place before hardening begins - usually 2 minutes
- Can be drilled, filed, taped, machined, ect., after one hour of curing time
- For underwater applications, work the mixed epoxy forcefully into the repair and hold until adhesion begins to take effect.

TIP: For a smooth surface, hand rub with water prior to hardening



WARNING - KEEP OUT OF REACH OF CHILDREN: Contains epoxy and amine resins that may cause irritation to the skin. Wash hands with soap and water after use. Eye irritant. In case of eye contact, flush with water. Contact physician. May be harmful if swallowed.



INSTRUCCIONES – LEA COMPLETAMENTE ANTES DE COMENZAR:

Para mantener limpias las manos, humedézcalas con agua antes de amasar.

- Para la mejor adherencia, limpie y haga más áspera la superficie de unión antes de la aplicación.
- Tuerza, rompa o corte la cantidad que necesita para la reparación.
- Amase la masilla hasta que tenga un color uniforme – sin ninguna mancha.
- La masilla debe estar en su lugar antes de que se empiece a endurecer, generalmente unos 2 minutos.
- Se puede taladrar, limar, agujerear, torneear, etc. después de una hora de su aplicación.
- Para aplicaciones en el agua, introduzca con fuerza la mezcla de epoxy en la reparación y manténgala en su lugar hasta que empiece a adherirse.

SUGERENCIA: Para uso en una superficie lisa, frote con la mano usando agua antes de que se endurezca.

ADVERTENCIA – SE DEBE MANTENER FUERA DEL ALCANCE DE NIÑOS: Contiene resinas de epoxy y amínicas que pueden irritar la piel. Hay que lavarse las manos con jabón y agua después de su uso. Irritante de los ojos. En el caso de que entre en contacto con los ojos, enjuague con agua y solicite atención médica. Puede ser nocivo si se ingiere.

